

PRODUCT DATA SHEET

SikaRapid[®]-1

Hardening accelerator for concrete and mortar

DESCRIPTION

SikaRapid[®]-1 is a liquid hardening accelerator for concrete and mortar. It meets the requirements for hardening accelerators according to GB8076, GB18588 and JC475. SikaRapid[®]-1 promotes early strength development without negatively influencing final strengths.

USES

SikaRapid[®]-1 is especially suitable for any application where fast early strength development plays a major role, or is of crucial importance within 6 to 24 hours. SikaRapid[®]-1 is used for the following applications:

- Precast concrete
- Ready- mixed concrete where early demoulding is essential
- Cold ambient temperatures to achieve sufficient strength gain
- Slip-formed concrete
- Ready- mixed concrete where minimum time delays are critical

CHARACTERISTICS / ADVANTAGES

SikaRapid[®]-1 provides the following advantages through accelerated hardening of the concrete:

- Faster turnaround of formwork in precast applications
- Reduced or eliminated heat or steam curing
- Fast construction processes and early load bearing capacity
- Continuous concreting at low temperatures
- No negative effects on the final strengths

When applied with a superplasticizer, SikaRapid[®]-1 will not change the fresh concrete properties produced by the superplasticizer.

SikaRapid[®]-1 does not contain chlorides or any other ingredients which promote the corrosion of steel. It is therefore suitable for use in reinforced concrete

PRODUCT INFORMATION

Composition	Mixture of organic and inorganic complex agents.
Packaging	1000 kg IBC container
Shelf life	12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Storage at temperatures between 5 °C and 30 °C. Protect from direct sunlight, frost and contamination.
Appearance and colour	Red liquid
Density	~1.17 kg/l (at +23°C)
pH-Value	8.5±1.0

PRODUCT DATA SHEET

SikaRapid[®]-1

March 2022, Version 01.02

02140202100000004

TECHNICAL INFORMATION

Concreting guidance	The standard rules of good concreting practice, concerning production and placing, are to be followed. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components. Fresh concrete must be cured properly and curing applied as early as possible.
----------------------------	--

APPLICATION INFORMATION

Recommended dosage	0.5 - 2.0 % by weight of cement
Dispensing	SikaRapid®-1 is added to the gauging water or added with it into the concrete mixer. SikaRapid®-1 may also be added into the ready-mix truck on site. When added on site the truck mixer shall rotate its drums at maximum revolutions for at least 1 minute per m ³ concrete and a minimum of 5 minutes to achieve a uniform mix. The concrete has to be visually checked for uniform consistence before discharging.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

When using SikaRapid®-1 a suitable mix design has to be produced and the local material sources shall always be trialled.
If frozen and/or if precipitation of the product has occurred, SikaRapid®-1 may be used after thawing slowly at room temperature and intensive mixing.
Before application, suitability tests must be performed.
It is advised against the application of SikaRapid®-1 in pre-tensioned pre-stressed concrete produced with the span bed method.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PRODUCT DATA SHEET
SikaRapid®-1
March 2022, Version 01.02
02140202100000004

SikaRapid-1-en-MN-(03-2022)-1-2.pdf

