

PRODUCT DATA SHEET

Sikadur®-30

Adhesive for bonding reinforcement

DESCRIPTION

Sikadur®-30 is a thixotropic, structural 2-component adhesive, based on a combination of epoxy resins and special filler, designed for use at normal temperatures between +8 °C and +35 °C.

USES

Sikadur®-30 may only be used by experienced professionals.

Adhesive for bonding structural reinforcement, particularly in structural strengthening works. Including:

- Sika® CarboDur® Plates to concrete, brickwork and timber (for details see the Sika® CarboDur® Product Data Sheet)
- Steel plates to concrete (for details see the relevant Sika Technical information).

CHARACTERISTICS / ADVANTAGES

Sikadur®-30 has the following advantages:

- Easy to mix and apply.
- No primer needed.
- High creep resistance under permanent load.
- Very good adhesion to concrete, masonry, stone-work, steel, cast iron, aluminium, timber and Sika® CarboDur® Plates.
- Hardening is not affected by high humidity.
- High strength adhesive.
- Thixotropic: non-sag in vertical and overhead applications.
- Hardens without shrinkage.
- Different coloured components (for mixing control).
- High initial and ultimate mechanical resistance.
- High abrasion and shock resistance.
- Impermeable to liquids and water vapour.

APPROVALS / CERTIFICATES

- Deutsches Institut fuer Bautechnik Z-36.12-29, 2006: General construction authorisation for Sika® CarboDur®.
- IBMB, TU Braunschweig, test report No. 1871/0054, 1994: Approval for Sikadur®-30 Epoxy adhesive.
- IBMB, TU Braunschweig, test report No. 1734/6434, 1995: Testing for Sikadur®-41 Epoxy mortar in combination with Sikadur®-30 Epoxy adhesive for bonding of steel plates.
- Adhesive for structural bonding tested according to EN 1504-4

PRODUCT INFORMATION

Composition	Epoxy resin	
Packaging	6 kg (A+B)	Pre-batched unit pallets of 480 kg (80 x 6 kg)
Shelf life	24 months from date of production	
Storage conditions	Store in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight.	
Colour	Part A: white Part B: black Part A+B mixed: light grey	
Density	1.65 kg/l ±0.1 kg/l (part A+B mixed) (at +23 °C)	

TECHNICAL INFORMATION

Compressive strength	Curing Time	Curing Temperature		(EN 196)
		+10 °C	+35 °C	
	12 hours	-	~85 N/mm ²	
	1 day	~55 N/mm ²	~90 N/mm ²	
	3 days	~70 N/mm ²	~90 N/mm ²	
	7 days	~75 N/mm ²	~90 N/mm ²	
Modulus of elasticity in compression	~9 600 N/mm ² (at 23 °C)			(ASTM D 695)
Tensile strength	Curing Time	Curing Temperature		(DIN EN ISO 527-3)
		+15 °C	+35 °C	
	1 day	~20 N/mm ²	~26 N/mm ²	
	3 days	~23 N/mm ²	~27 N/mm ²	
	7 days	~26 N/mm ²	~29 N/mm ²	
Modulus of elasticity in tension	~11 200 N/mm ² (+23 °C)			(ISO 527)
Shear strength	Concrete failure (~15 N/mm ²)			(FIP 5.15)
	Curing time	Curing Temperature		
		+15 °C	+35 °C	
	1 day	~4 N/mm ²	~17 N/mm ²	
	3 days	~15 N/mm ²	~18 N/mm ²	
	7 days	~16 N/mm ²	~18 N/mm ²	
	18 N/mm ² (7 days at +23C) According to DIN 53283			
Shrinkage	0.04 %			(FIP: Fédération Internationale de la Précontrainte)
Coefficient of thermal expansion	2.5 x 10 ⁻⁵ per °C (Temperature range: -20 °C to +40 °C)			
Service temperature	-40 °C to +45 °C (when cured at +23 °C)			
Glass transition temperature	Curing time	Curing temperature	TG	(EN 12614)
	7 days	+45 °C	+62 °C	

Heat deflection temperature

Curing time

Curing temperature

HDT

(ASTM-D 648)

3 hours	+80 °C	+53 °C
6 hours	+60 °C	+53 °C
7 days	+35 °C	+53 °C
7 days	+10 °C	+36 °C

APPLICATION INFORMATION

Mixing ratio	Component A : Component B = 3 : 1 by weight or volume When using bulk material the exact mixing ratio must be safeguarded by accurately weighing and dosing each component.		
Layer thickness	30 mm max. When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.		
Sag flow	On vertical surfaces it is non-sag up to 3–5 mm thickness at 35 °C	(FIP: Fédération Internationale de la Précontrainte)	
Squeezability	4'000 mm ² at +15 °C at 15 kg (FIP: Fédération Internationale de la Précontrainte)		
Material temperature	Sikadur®-30 must be applied at temperatures between +8 °C and +35 °C.		
Ambient air temperature	+8 °C min. / +35 °C max.		
Dew point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.		
Substrate temperature	+8 °C min. / +35 °C max.		
Substrate moisture content	Max. 4 % pbw When applied to mat damp concrete, brush the adhesive well into the substrate.		
Pot Life	Temperature	Potlife	Open time (FIP: Fédération Internationale de la Précontrainte)
	+8 °C	~120 minutes	~150 minutes
	+20 °C	~90 minutes	~110 minutes
	+35 °C	~20 minutes	~50 minutes

The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill components A+B before mixing them (not below +5 °C).

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Sikadur® resins are formulated to have low creep under permanent loading. However, due to the creep behavior of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20–25 % of the failure load.

A structural engineer must be consulted for load calculations for the specific application.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

See the Product Data Sheet of Sika® CarboDur® Plates and Sika® CarboDur® BC rods.

SUBSTRATE PREPARATION

See the “Method Statement for Sika® CarboDur® Ex-



ternally Bonded Reinforcement” Ref: 850 41 05 and the “Method Statement for Sika® CarboDur® Near Surface Mounted Reinforcement” Ref: 850 41 07.

MIXING

Pre-batched units:

Mix components A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour.

Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.

Bulk packing, not pre-batched:

First, stir each component thoroughly. Add the components in the correct proportions into a suitable mixing pail and stir correctly using an electric low speed mixer as above for pre-batched units.

APPLICATION METHOD / TOOLS

See the “Method Statement for Sika® CarboDur® Externally Bonded Reinforcement” Ref: 850 41 05 and the “Method Statement for Sika® CarboDur® Near Surface Mounted Reinforcement” Ref: 850 41 07.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PRODUCT DATA SHEET

Sikadur®-30

March 2022, Version 04.01

020206040010000001

Sikadur-30-en-MN-(03-2022)-4-1.pdf