

PRODUCT DATA SHEET

Sika® Antisol® S

Concrete Curing Compound

DESCRIPTION

Sika® Antisol® S is a ready to use solvented spray applied liquid curing agent to prevent water loss from the surface of freshly placed concrete. It forms a micro-crystalline seal in the concrete pores reducing the moisture evaporation rate from the concrete mix. Adhesion of subsequent treatments to concrete surface is not impaired.

USES

Treatment of vertical surfaces which will require subsequent treatments or where resin / water based curing membranes would be unsuitable.

Exposed concrete such as:

- Buildings
- Manufacturing industries
- Hangars and loading areas
- Retaining walls
- Pre-stressed structures
- Irrigation channels
- Civil Engineering structures

Sika® Antisol® S may be applied to "green" concrete to increase the density of the cured surface thus improving its subsequent durability.

CHARACTERISTICS / ADVANTAGES

- Generally improves the surface appearance
- Reduces cracking
- Assists reaching the required strengths
- Reduces shrinkage
- Controls cement hydration
- Reduces dust formation
- Reduced concrete permeability
- Alleviates other costly curing methods
- Adhesion of subsequent treatments to concrete surface is not impaired.

PRODUCT INFORMATION

Packaging	25 kg/pail and 1000 kg/IBC container
Shelf life	12 months from date of production
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
Appearance and colour	Transparent liquid
Density	~1,08±0,05 kg/l

APPLICATION INFORMATION

Consumption	4-5 m ² /ltr. Consumption depends on wind speed, temperature and humidity during application. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.
--------------------	--

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- It is recommended that Sika® Antisol® S should be applied at the earliest practical time after the concrete surface is ready to receive the curing compound.
- To prevent the nozzle from blocking, regularly clean the spraying equipment during application.
- After application protect from direct sunlight, severe dry wind or rain for at least 2–3 hours, depending on the ambient conditions.
- Remaining surface film must be removed before the application of any additional screed or coating.
- Where a highly durable abrasion resistant surface is required, i.e. in severe exposure conditions, apply a further coat of Sika® Antisol® S after 3 days. Subsequent surfacing systems can be applied after 7 days.
- Early application of Sika® Antisol® S will help reduce plastic shrinkage cracks from occurring by reducing the amount of water evaporating. Concrete curing compounds, however, will not counter the effects of cracking that may occur as a result of long term drying shrinkage. Standard concrete practice must apply when positioning construction joints and shrinkage control joints.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surface must be free from surface water. Evaporation of the surface water can take from 30 minutes to 2 hours, depending on temperature and water / cement ratio.

APPLICATION

Vertical Surfaces

After removing the formwork, dampen down the concrete thoroughly with fresh water allowing the surface water to drain off. Spray product in a fine mist to completely cover the concrete surface. Maintain the pressure in the application equipment to ensure a consistent spray.

Horizontal Surfaces

Spray product in a fine mist to completely cover the concrete surface. Maintain the pressure in the application equipment to ensure a consistent spray.

All Surfaces

If the concrete is exposed to direct sunlight with high temperatures (plus 23°C) or severe dry wind, protect the surface with the polyethylene sheet of 2-3 hours after applying Sika® Antisol® S to allow time for crystal formation. The polyethylene sheet should be in direct contact with the surface to maximize the benefits.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PRODUCT DATA SHEET

Sika® Antisol® S

April 2022, Version 01.02

02140503100000008

SikaAntisolS-en-MN-(04-2022)-1-2.pdf