

PRODUCT DATA SHEET

SikaInject[®]-684

Highly Reactive, Thixotropic Polyurea Silicate Injection Resin

DESCRIPTION

SikaInject[®]-684 is a fast reacting, thixotropic 2-component polyurea silicate injection resin specifically designed for rock bolt anchoring (RBA) and cable-bolt installations.

The extended setting time allows the installation in areas with higher ambient temperature and where longer open times are required.

USES

SikaInject[®]-684 may only be used by experienced professionals.

- Resin-into-bolt rock bolting at all angles
- Bolt-into-resin rock bolting at all angles
- Suitable for steel and glass-fiber bolts

FEATURES

- Extended setting time, for areas with higher ambient temperatures
- Over head application without additional sealing
- Secure and precise injection due to its thixotropic properties
- Flexibility in application and long-distance pumping capacity
- Penetrates cracks down to 0.14 mm
- Increased reliability due to its full-size grouting
- Safe and easy mixing, even in low temperatures >5°C
- High structural strength combined with flexibility
- Good adhesion to damp and low friction substrates
- Volume-stable, no expansion upon water contact, no water absorption
- Fast curing and fast strength development = improved work safety
- Fire resistant according to DIN 4102-2 Class B2

PRODUCT INFORMATION

Packaging	25 l cans / 200 l drums / 1000 l IBC / specials on request
Colour	Part A: Colorless, liquid Part B: Dark brown, liquid
Shelf life	24 months from date of production
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperature between +5 °C and +35 °C.
Density	Part A: 1.39 kg/l (20°C) Part B: 1.18 kg/l (20°C)
Viscosity	Part A: 490 mPa.s (23°C) Part B: 150 mPa.s (23°C)

TECHNICAL INFORMATION

Compressive strength	> 35 MPa (23°C)
Expansion	1 (foam expansion factor)
Resistance to fire	Class B2 (DIN 4102-2)

APPLICATION INFORMATION

Mixing ratio	1:1 parts by volume
Reaction time	250 s - 310 s (setting time, 23°C), thixotropic effect = immediately

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

Part A and part B are delivered ready to use. Inject them in mixing ratio of 1:1 parts by volume using a 2-component injection pump equipped with a static inline mixer nozzle. For optimal mixing of the components use a min. 32 cm static-in-line mixer in connection with the mixing head. The static mixer should at least consist of 16 crossmixing elements. Note: curing time is depends on temperature of product and ground. Store both components prior to application at least at +10°C.

CLEANING OF EQUIPMENT

- For short breaks in the injection procedure, pump part A through the in-line static mixer nozzle
- After the injection process rinse pump with suitable cleaning agent (e.g. SikaInject®-CL2) or waterfree low-viscosity hydraulic oil
- Flush pump and injection hoses until SikaInject®-684 is completely washed out
- Store pump and hoses filled with oil and seal all openings

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PRODUCT DATA SHEET
SikaInject®-684
June 2026, Version 01.01
020707070020000022

SikaInject-684-en-MN-(06-2026)-1-1.pdf

