

PRODUCT DATA SHEET

Sikafloor®-348 Level Overlayment

High Strength Shrinkage Compensated Self-Smoothing Cementitious Topping

DESCRIPTION

Sikafloor®-348 Level Overlayment is a fast setting flow applied cementitious topping that is ideal for levelling screeds in preparation for trafficked coatings, direct trafficking or polishing. Shrinkage compensated, strong and fast curing it can accept foot traffic after about 8 hours, can be directly trafficked or can accept most resin based coatings.

With close adherence to the simple mixing and installation instructions Sikafloor®-348 Level Overlayment produces a smooth trafficable finish. It is compatible with most commonly used floor hardeners, coatings, adhesives, carpet, linoleum and similar floor finishes as well as with hard wood flooring, ceramic tiles etc.

USES

Levelling screed for the installation of :

- Polyurethane floorings
- Epoxy floorings
- Vinyl floorings
- Ceramic floorings

PRODUCT INFORMATION

Packaging	25 kg bag
Shelf life	6 months from the date of production
Storage conditions	Stored properly in undamaged and unopened original sealed packaging in the dry conditions. Protect from direct sunlight and frost.
Appearance and colour	Grey

TECHNICAL INFORMATION

Compressive strength	> 12 MPa at 24 hours ; > 25 MPa at 28 day
Tensile strength in flexure	> 8 MPa at 28 days
Tensile adhesion strength	> 1 MPa at 28 days

APPLICATION INFORMATION

Yield	Approx. 16 litres, suitable for 3.2 m ² per bag @ 5 mm thick
Layer thickness	Approx. 5–30 mm

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The condition of the surface to be treated is of great importance. The substrate must be mechanically prepared e.g. scabbled, milled or shot blasted. All laitance and contamination must be removed to leave a clean aggregate exposed finish. Testing and assessment to BS8204 Part 3 1993 should be conducted before proceeding with vacuum cleaning, sealing and priming. To seal and prime the concrete surface prior to installation use Sikafloor®-12 Primer in accordance with the data sheet and allow the primer to dry. Failure to prime the surface properly will result in blemishes and pinholes in the surface.

MIXING

Sikafloor®-348 Level Overlayment is mixed with the specified quantity of clean, potable water using the appropriate forced action mixer or pump equipment. For hand mixing the material should be mixed with a low or medium speed drill and paddle for at least 2 minutes and until free from lumps. The material should then be left for 5 minutes and briefly remixed for 30 seconds before being poured into place. For pump mixing the flow rate should be adjusted to achieve the initial flow of ~ 140 mm. A PFT G5 pump with a 20 metre hose has been found suitable. The water addition should be closely equivalent to 6 litres per 25 kg bag.

APPLICATION

After pouring or pumping the mixed material onto the primed substrate the material should be levelled to the desired thickness using a pin leveler, squeegee, notched trowel or similar. Subsequent mixes should be applied onto a wet edge and similarly levelled. Use the equipment to move the material into corners, low spots and around fittings. As soon as the level has been achieved and before the material starts to lose

workability use a spiked roller to help any trapped air travel to the surface. Failure to do this will result in pinholes and blemishes in the surface.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with clean water immediately after use. Cured material can be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PRODUCT DATA SHEET
Sikafloor®-348 Level Overlayment
March 2022, Version 01.03
020815020010000009

Sikafloor-348LevelOverlayment-en-MN-(03-2022)-1-3.pdf